



## EUROPE SEALS BV

### TEST REPORT

#### PERFLUOROELASTOMER CLEAR 70 Sh

#### Original Physical Properties Requirements Results

Hardness, (Shore A ) (ASTM D2240) **70±5 72**

Tensile Strength,(Mpa),min (ASTM D1414) **17.3**

Elongation, % ,min (ASTM D1414) **238**

Modulus at 100%, (Mpa),min (ASTM D1414) **4.1**

Specific Gravity (g/cm<sup>3</sup>) **2.052**

**Compression Set, 70 Hrs @ 200°C (ASTM D395,Method B), max.(AS-214) 32**

**Compression Set, 70 Hrs @ 230°C (ASTM D395,Method B), max.(AS-214) 42**